

## Self-Furring Dimple Lath

### 1/4" Self-furring, dimpled, expanded steel plaster and stucco base

A self-furring expanded dimpled metal lath ideal for interior and exterior use over sheathing, masonry, and other solid surfaces as required per ASTM C847, ASTM C1780, ASTM C1063. The 1/4" dimpled furring allows for more thorough plaster or stucco embedment into and behind the lath for superior mechanical bonding.

The dimple-patterned, self-furring plaster base is manufactured with evenly spaced indentations that hold the metal lath 1/4" away from the surface to be plastered. This results in an even and thorough embedment of the plaster.

The dimples are spaced every 4"-6" over the rectangular sheet. This lath is ideal for manufactured stone installations per ASTM C1780 or typical plaster applications per ASTM C1063.

2.5# and 3.4# self-furring dimple lath is available with G90 coating with a special order and lead time. Self-furring dimple lath is also available with a 60-Minute Grade-D asphalt paper-backing (APB) weather resistant barrier.

### Product Data & Ordering Information:

**Material:** G60 Galvanized Steel

**Packaged:** 25 bundles or 250 pieces per pallet

Product Code	Wt. per Sq. Yd.	Sheet Size	Pcs./Bdl.	Yds./Bdl.	Yds./Pallet
LAD	2.5 lbs.	27" x 97"	10	20	500
LAD	3.4 lbs.	27" x 97"	10	20	500

### Code Approvals & Performance Standards

- [ASTM A653](#) Standard Specification for Steel Sheet, Zinc-Coated (Galvanized) or Zinc-Iron Alloy-Coated (Galvannealed) by the Hot-Dip Process
- [ASTM C847](#) Standard Specification for Metal Lath
- [ASTM C1063](#) Standard Specification for Installation of Lathing and Furring to Receive Interior and Exterior Portland Cement-Based Plaster
- [ASTM C1780](#) Standard Practice for Installation Methods for Cement-based Adhered Masonry Veneer
- [Intertek CCRR-0204](#) Metal Lath - Code Compliance Research Report
- [SDS For ASTM A653 Steel Finishing Products](#) For Interior Finishing and Exterior Finishing

### Storage:

All stored materials shall be kept dry. Materials shall be stacked off the ground, supported on a level platform, and protected from the weather and surface contamination per ASTM C847 & C1063.

### Limitations:

Galvanized steel products should not be used with magnesium oxychloride cement stucco or Portland cement stucco containing calcium chloride additives.

**Sustainability Credits** For more details and LEED letters contact Technical Services at 888-437-3244 or visit [clarkdietrich.com/LEED](http://clarkdietrich.com/LEED).

- **LEED v4.1 MR Credit:** Environmental Product Declarations: EPD (1 point) - Sourcing of Raw Materials (up to 2 points) - Material Ingredients (1 point) - Construction and Demolition Waste Management (up to 2 points)
- **LEED v4 MR Credit:** Building Product Disclosure and Optimization: EPD (1 point) - Sourcing of Raw Materials (1 point) - Material Ingredients (1 point) - Construction and Demolition Waste Management (up to 2 points) - Innovation Credit (up to 2 points).

