Paper-Backed (APB) Dimple Self-Furring Lath

Galvanized expanded steel plaster/stucco base



A superior mesh multi-purpose expanded steel base with an approved Grade-D weather resistant barrier attached. Application of asphalt paper-backed (APB) metal lath is used behind stone, traditional stucco, and tile installations as a code compliant weather resistant barrier. It provides protection against wet areas during stucco curing. Paper-Backed Lath comes in flat and self-furring configurations to accommodate your installation needs.

APB is available with Diamond Metal Lath, Self-Furring Dimple Lath and Self-Furring V-Groove Lath.

Optional 60-minute Grade-D paper available for higher weather resistance and durability.

The asphalt paper-backed weather resistant barrier meets Federal Specification UUB790A: Type 1, Grade-D, Style 2 and is printed on the face of the paper for easy identification.

Product Data & Ordering Information:

Material: G60 Galvanized Steel
Type 1, Grade-D, Style 2 Paper
Packaged: 25 bundles or 250 pieces per pallet

Product Code	Wt. per Sq. Yd.	Sheet Size	Sheets/Bundle	Bundle/Pallet
LAD(O)	2.5 lbs.	27" x 97"	10	25
LAD(O)	3.4 lbs.	27" x 97"	10	25



Code Approvals & Performance Standards

- ASTM A653 Standard Specification for Steel Sheet, Zinc-Coated (Galvanized) or Zinc-Iron Alloy-Coated (Galvannealed) by the Hot-Dip Process
- ASTM C841 Standard Specification for Installation of Interior Lathing and Furring
- ASTM C847 Standard Specification for Metal Lath
- ASTM C1063 Standard Specification for Installation of Lathing and Furring to Receive Interior and Exterior Portland Cement-Based Plaster
- Federal Specification UU-B-790A Building Paper, Vegetable Fiber (Kraft, Waterproofed, Water Repellant and Fire resistant)
- Intertek CCRR-0204 Metal Lath - Code Compliance Research Report
- SDS For ASTM A653 Steel Finishing Products For Interior Finishing and Exterior Finishing

Storage:

All stored materials shall be kept dry and out of the weather. Materials shall be stacked off the ground, supported on a level platform, and protected from the weather and surface contamination per ASTM C847 & C1063. Paper-backed lath should not be stored outside where ran water can become trapped between sheets, thereby oxidizing the metal.

Limitations:

Galvanized steel products should not be used with magnesium oxychloride cement stucco or Portland cement stucco containing calcium chloride additives.

Sustainability Credits For more details and LEED letters contact Technical Services at 888-437-3244 or visit clarkdietrich.com/LEED.

- **LEED v4.1 MR Credit:** Environmental Product Declarations: EPD (1 point) - Sourcing of Raw Materials (up to 2 points) - Material Ingredients (1 point) - Construction and Demolition Waste Management (up to 2 points)
- **LEED v4 MR Credit:** Building Product Disclosure and Optimization: EPD (1 point) - Sourcing of Raw Materials (1 point) - Material Ingredients (1 point) - Construction and Demolition Waste Management (up to 2 points) - Innovation Credit (up to 2 points).